

FLORIDA
REF F

RECOMMENDED FOR
Contract use

COMPOSITION
Raw hide leather (corrected grain)
through dyeing aniline

TEAR RESISTANCE
>20N (UNI EN ISO 3377-1)

CRACK RESISTANCE
50.000 Cycles (UNI EN ISO 5402)


DRY RUB FASTNESS
1.000 Cycles Vol. >4 Grey scale
(UNI EN ISO 11640)

LIGHT FASTNESS
Vol. >6 Blue scale
(UNI EN ISO 105-B02)

FIRE TEST
BS 5852-0 - BS 5852-1
BS5852 CRib5 (optional)
UNI EN 1021-1
UNI EN 1021-2
NFPA 260/UFAC
California TB 117 Section E -AB-2998




Example: F55 - GREEN



F10 - BLACK



F15 - CAMEL



F54 - WHITE



F55 - GREEN

