


PANAMA
REF P


RECOMMENDED FOR Contract use	WET RUB FASTNESS 250 Cycles / Vol. 5 Grey scale (ISO 11640)
COMPOSITION Raw hide leather (corrected grain)	LIGHT FASTNESS 72 h. exposition / Vol. 5 Grey scale (EN ISA 105-B02)
TEAR RESISTANCE 20N (EN3377-1)	FIRE TEST BS 5852-0 - BS 5852-1 BS5852 CRib5 (optional) UNI EN 1021-1 UNI EN 1021-2 NFPA 260/UFAC California TB 117 Section E - AB-2998
CRACK RESISTANCE 50.000 Cycles (EN ISO 5402)	
DRY RUB FASTNESS 1.000 Cycles / Vol. 5 Grey scale (ISO 11640)	




Example: P01 - Sand



P01 - SAND



P10 - BLACK



P15 - DARK BROWN